

# nVent LENTON Ultimate Mechanical Anchors Independent Test Data for ASTM® A706 Grade 80



## DR16 SERIES - HEAD AREA EXCEEDS 5X BAR AREA (NET 4X)

Part Numbers	Rebar			Independent Test Lab Results			IBC, ACI 318, ASTM A970	
	Size	Area (in <sup>2</sup> )	Report Number	Tested Results* (psi)	% f <sub>y</sub>	Code Requirements 100% f <sub>u</sub> (100,000) psi	Class A, B, & HA Pass/Fail	
	in-lb							mm
LU12DR16	4	12	0.20	TK4073	118,135	148%	100,000	Pass
				TK4074	121,585	152%		Pass
				TK4075	118,860	149%		Pass
LU16DR16	5	16	0.31	TK4084	118,587	148%	100,000	Pass
				TK4085	117,858	147%		Pass
				TK4086	117,997	148%		Pass
LU20DR16	6	20	0.44	TK4099	117,064	146%	100,000	Pass
				TK4101	116,798	146%		Pass
				TK4102	117,384	147%		Pass
LU22DR16	7	22	0.60	TK4470	116,550	146%	100,000	Pass
				TK4471	116,510	146%		Pass
				TK4472	116,212	145%		Pass
LU25DR16	8	25	0.79	TK4475	124,309	155%	100,000	Pass
				TK4476	127,038	159%		Pass
				TK4477	124,911	156%		Pass
LU28DR16	9	28	1.00	TK4177	114,715	143%	100,000	Pass
				TK4178	117,285	147%		Pass
				TK4179	114,729	143%		Pass
LU32DR16	10	32	1.27	TK4111	115,098	144%	100,000	Pass
				TK4150	114,732	143%		Pass
				TK4151	114,451	143%		Pass
LU36DR16	11	36	1.56	TK4154	115,337	144%	100,000	Pass
				TK4155	115,341	144%		Pass
				TK4156	116,234	145%		Pass
LU43TMT12 & EL43TD16	14	43	2.25	TK4505	109,966	138%	100,000	Pass
				TK4506	110,336	138%		Pass
				TK4507	110,403	138%		Pass
LU57TMT12 & EL57TD16	18	57	4.00	TK4592	108,565	136%	100,000	Pass
				TK4593	110,414	138%		Pass
				TK4595	110,497	138%		Pass

\* Tested performance also exceeds ACI 318 & ASTM A970 for ASTM A706 Grade 60 and A615 Grades 60, 75 and 80.

### Definitions:

ACI 318, Section 20.2.1.6 - Headed Deformed bars shall conform to ASTM A970, including Annex A1 requirements for Class HA head dimensions.

ASTM A970 requirements:

Class A, Section 6.3.1.1 – Develop the minimum specified tensile strength of the reinforcing bar

Class B, Section 6.3.1.2 – Develop the minimum specified tensile strength and the minimum specified elongation of the reinforcing bar

Class HA, Section A1.2.1 – Develop the minimum specified tensile strength of the reinforcing bar

### Notes:

Table is a summary of Benchmark Holdings International independent laboratory tests. Test reports available upon request.

DR16 Series - 4x net area



Our powerful portfolio of brands:

**CADDY ERICO HOFFMAN RAYCHEM SCHROFF TRACER**

[nVent.com/LENTON](http://nVent.com/LENTON)

WARNING: nVent products shall be installed and used only as indicated in nVent's product instruction sheets and training materials. Instruction sheets are available at [nVent.com/LENTON](http://nVent.com/LENTON) and from your nVent customer service representative. Improper installation, misuse, misapplication or other failure to completely follow nVent's instructions and warnings may cause product malfunction, property damage, serious bodily injury and death and/or void your warranty.

©2018 nVent. All nVent marks and logos are owned or licensed by nVent Services GmbH or its affiliates. All other trademarks are the property of their respective owners. nVent reserves the right to change specifications without notice. LENTON-FLY-HB4303-Ultimate-EN-1810